

食品接觸級 SAN, KIBISAN[®] PN-127 L150 FG**加工建議條件**


A 乾燥 : 75~80°C, 3~4 小時。

依以下變數而變 a)濕度

b)回收料比例

c)儲存條件

B.射出機套筒(Barrel)設定溫度



C. 模具溫度 40~60 °C。

依以下變數而變 a)製品厚度

b) 尺寸

c) 澆口(Gate)及流道(Runner)系統

D. 射壓 50~70 kg/cm²

保壓 40~60 kg/cm²

背壓 5~15 kg/cm²

備註：

1. 生產及操作時避免樹脂接觸到灰塵及雜物。
2. 在射出週期中勿將熱融膠(Hot Melt)長期停留在加熱管中。
3. 熱澆道之系統溫度不可超過230°C以免材料劣化。
4. **轉料/洗俾時不可使用非食品接觸級之樹脂。**
5. 若有任何疑問請洽06-2665000, 06-2663000

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHI MEI CORPORATION at the date of issue. CHI MEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHI MEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHI MEI CORPORATION. In no event will CHI MEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.